

Price list – HCB hempcrete blocks (density 330 kg/m³)

Non load-bearing, vapour-permeable, better-than-zero-carbon natural insulation blocks

**HCBlock dimensions: 50 cm (L) x 20 cm (H) x varying thicknesses
(as shown below)**

Block thickness (cm)	No. of blocks per pallet	m ² per pallet	Price per m ² (£)	Price per pallet (£)
8	142	14.2	26.26	372.90
12	122	12.2	39.49	481.80
15	102	10.2	49.50	504.90
25	62	6.2	82.50	511.50
30	52	5.2	99.00	514.80
36	42	4.2	118.64	498.30
40	42	4.2	132.00	554.40

Please note: Prices shown above exclude VAT and delivery. Blocks are sold in full pallets only. Minimum order quantities and 60 day lead in time may apply, depending on stock levels at time of ordering.

Technical information for HCB hempcrete blocks

Technical data issued in April 2015

Thickness in cm	8	12	15	25	30	36	40
Density in kg/m ³	330	330	330	330	330	330	330
λ Thermal conductivity in W/(mK)	0.07	0.07	0.07	0.07	0.07	0.07	0.07
Thermal transmittance (U-value) in W/(m ² K)	0.76	0.53	0.43	0.27	0.22	0.19	0.17
Resistance to water vapour diffusion (m)	4.50	4.50	4.50	4.50	4.50	4.50	4.50
Specific heat capacity (J/kgK)	1870	1870	1870	1870	1870	1870	1870
Coefficient of sound absorption	0,8	0,8	0,8	0,8	0,8	0,8	0,8
Sound reduction index, Rw (dB) with 1.5 cm of plaster per side	24.37	36.55	37.51	40.11	41.17	42.29	42.96
Reaction to fire with plaster	Non-flammable		Non-flammable	Non-flammable		Non-flammable	
Phase shift without plaster	3h09'	5h53'	7h58'	14h48'	18h13'	22h19'	25h04'

For more information or for delivery prices and lead times, please contact us on: 01629 343 143 or via: <https://www.ukhempcrete.com/services/material-supply/>

Price list date: 20 Sept 2016